

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
22 April 2004 (22.04.2004)

PCT

(10) International Publication Number
WO 2004/033740 A1

- (51) International Patent Classification⁷: **C22C 21/12**
- (21) International Application Number:
PCT/JP2003/012938
- (22) International Filing Date: 9 October 2003 (09.10.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
2002-296268 9 October 2002 (09.10.2002) JP
60/483,635 1 July 2003 (01.07.2003) US
- (71) Applicant (*for all designated States except US*): **SHOWA DENKO K.K.** [JP/JP]; 13-9, Shiba Daimon 1-chome, Minato-ku, Tokyo 105-8518 (JP).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **YOSHIOKA, Hiroki** [JP/JP]; c/o Oyama Regional Office, SHOWA DENKO K.K., 480, Inuzuka 1-chome, Oyama-shi, Tochigi 323-0811 (JP). **YAMANAKA, Masaki** [JP/JP]; c/o Oyama Regional Office, SHOWA DENKO K.K., 480, Inuzuka 1-chome, Oyama-shi, Tochigi 323-0811 (JP). **MATSUOKA, Hideaki** [JP/JP]; B-101, 1010 Yamagoe, Nagakute-cho, Aichi-gun, Aichi 480-1111 (JP).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— with international search report
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: ALUMINUM ALLOY FOR CUTTING PROCESSING, AND ALUMINUM ALLOY WORKED ARTICLE MADE OF THE SAME

(57) Abstract: An aluminum alloy for cutting processing consists essentially of Cu: 1 to 6.5 mass%, Zn: 0.05 to 1 mass%, Bi: 0.1 to 1 mass%, Sn: 0.1 to 1 mass%, B: 100 mass ppm or less, or further includes at least one element as a selective additional element selected from the group consisting of Fe: 0.05 to 1 mass%, Mg: 0.01 to 0.3 mass%, Si: 0.05 to 1 mass% and Ti: 0.01 to 0.5 mass%.

WO 2004/033740 A1